



# DATA SHEET

N° 40/NG08 - R. 03 - 28/11/2017

Mod. 03 PGSQ 7.5\_01 Rev. 01 del 27.04.2017



1071-CPR

## GEO PP 4NG/08











Geo&tex 2000 S.p.A., Via XXV Aprile 3, I-36020 SAN NAZARIO (VI), Italy  
Produced in factories SN - CB1 - CB2

13


1071 - CPR - 1970

Non woven Geotextile manufactured from UV-stabilised polypropylene staple fiber, needlepunched and thermocalendered

INTENDED USES:

<input checked="" type="checkbox"/>		<b>EN ISO 13249:2016</b> Characteristics required for use in the construction of roads and other trafficked areas	<input checked="" type="checkbox"/>		<b>EN ISO 13250:2016</b> Characteristics required for use in the construction of railways
<input checked="" type="checkbox"/>		<b>EN ISO 13251:2016</b> Characteristics required for use in earthworks, foundations and retaining structures	<input checked="" type="checkbox"/>		<b>EN ISO 13252:2016</b> Characteristics required for use in drainage systems
<input checked="" type="checkbox"/>		<b>EN ISO 13253:2016</b> Characteristics required for use in erosion control works (coastal protection, bank revetments)	<input checked="" type="checkbox"/>		<b>EN ISO 13254:2016</b> Characteristics required for use in the construction of reservoirs and dams
<input checked="" type="checkbox"/>		<b>EN ISO 13255:2016</b> Characteristics required for use in the construction of canals	<input type="checkbox"/>		<b>EN ISO 13256:2016</b> Characteristics required for use in the construction of tunnels and underground structures
<input checked="" type="checkbox"/>		<b>EN ISO 13257:2016</b> Characteristics required for use in solid waste disposal	<input checked="" type="checkbox"/>		<b>EN ISO 13265:2016</b> Characteristics required for use in liquid waste containment projects

FUNCTIONS:



Characteristic	Test Method	Unit	Nominal Value	Tolerance	
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	255	-26	
Thickness	EN ISO 9863-1	mm	2 kPa	NPD	
Wide-Width tensile strength	EN ISO 10319	kN/m	MD	21,50	-2,00
			CMD	22,50	-2,00
			DIAG	NPD	NPD
Elongation	EN ISO 10319	%	MD	46,00	-9,2 / +30
			CMD	54,00	-10,8 / +35
			DIAG	NPD	NPD
Energy Index	EN ISO 10319	kN/m	≥4,5	NPD	
Static puncture resistance	EN ISO 12236	N	3300	-330	
Dynamic perforation test	EN ISO 13433	mm	17,0	+ 4,0	
Pyramidal puncture resistance	NF G 38019	kN	NPD	NPD	
Supported Pyramidal Puncture Resistance	EN 14574	N	NPD	NPD	
Characteristic opening size - O90	EN ISO 12956	µm	55	-16 / +16	
Permeability normal to the plane	EN ISO 11058	m/s	0,030	-0,009	
Long term protection efficiency	EN 13719	%	300 kPa	NPD	NPD
			600 kPa	NPD	NPD
			1200 kPa	NPD	NPD
Water flow capacity in the plane	EN ISO 12958	m <sup>2</sup> /s	20 kPa - i=1	NPD	NPD
			100 kPa - i=1	NPD	NPD
			200 kPa - i=1	NPD	NPD
Durability prediction	EN 13249/57:2016,ANNEX B EN 13265:2016,ANNEX B	To be covered within 1 month after installation. Predicted to be durable for more than 25 years in natural soils with 4<ph<9 and soil temperature < 25 °C			
Chemical resistance	EN 14030	Residual strength	MD	>90%	
Microbiological resistance	EN 12225	Residual strength	CMD	>90%	
			MD	100%	
			CMD	100%	


MD : Machine Direction - CMD : Cross Machine Direction - NPD: No performance determined / declared


TOLERANCE ON ROLL WIDTH: ± 3 cm. TOLERANCE ON ROLL LENGTH: ± 2% IF LENGTH ≤ 200 m, ± 1% IF LENGTH > 200 m.

STANDARD CORES: PAPER, DIAMETER INNER 71mm / OUTER 78mm ± 5%.

TECHNICAL DATA BASED ON STATISTIC ANALYSIS ON 95% CONFIDENCE LIMIT. PRESENT DATA SHEET CAN BE MODIFIED WITHOUT PRIOR NOTICE

Production plant codes: SN: 36020 San Nazario, Via XXV Aprile 3 - CB1: 36020 Campolongo Sul Brenta, Via Zannini 128 - CB2: 36020 Campolongo Sul Brenta, Via Giusti 54/56

Date	Issued	COM
28/11/2017		

Date	Verified	RCQ
28/11/2017		

Date	Approved	RSQ
28/11/2017		



Geo&tex 2000 S.p.A., Via XXV Aprile 3, I-36020 San Nazario (VI)- ITALY  
Tel. +39 (0)424 98330 - Fax. +39 (0)424 98593  
www.geotex2000.com - info@geotex2000.com

